

SLUMP REDUCER 1000P

POWDERED VISCOSITY MODIFYING ADMIXTURE FOR CONCRETE

PRODUCT DESCRIPTION: Slump Reducer 1000P is a powdered viscosity modifying agent designed to thicken high slump (wet) concrete and allow proper placement and finishing. Slump Reducer 1000P works by thickening the water in the mix, which allows improved suspension of the cement and sand aggregates, thereby providing controlled slump reduction. Slump Reducer 1000P is made with environmentally safe ingredients and is packaged in pre-measured individual bags for easy addition to mixer.

BENEFITS: ALLOWS CONTROLLED SLUMP REDUCTION ...IDEAL FOR CONCRETE PLACEMENT ON INCLINES OR IN SLIP FORMED CURBING POURS...ALLOWS FOR IMPROVED FINISHING WITH REDUCED BLEED AND SEGREGATION...ALLOWS FASTER DISCHARGE OF CONCRETE FROM TRUCKS ...IDEAL FOR MAKING QUICK SLUMP ADJUSTMENTS IN THE FIELD...PERMITS PLACING DIFFERENT SLUMPS FROM THE SAME LOAD...PREMEASURED BAGS ENSURE CONSISTENT RESULTS

COMPOSITION: Proprietary powdered VMA. Slump Reducer 1000P does not contain any air entraining agents or calcium chloride or intentionally added chlorides that would initiate or promote corrosion of reinforcement steel, or contribute to efflorescence.

TECHNICAL DATA: Slump Reducer 1000P is compatible with all conventional cement based admixtures and will not alter set times, compressive strengths, or air entrainment results. When used with other admixtures, each additive should be made separately into the mixer to allow for proper dispersion and reaction.

RECOMMENDED ADDITION RATES: Dosage of Slump Buster 1000P is typically one 8 ounce (227 gram) bag per every 4 yards of concrete for each 2-3 inches of slump reduction required. Lean (low cement) concrete mixes, gap graded or high sand concrete mixes will require higher dosages. Specco recommends a trial mix be conducted if possible with actual production materials in order to determine the optimum dosage for specific job site conditions. Refer to Cautions Section for additional information.

DIRECTIONS: Add the required amount of the Slump Buster 1000P bags to the mixer depending on the total yards and the amount of slump required. Let the mixer turn for at least 5 minutes on high speed, followed by 5 minutes on low speed to ensure proper thickening development and uniformity of the mix .

CAUTIONS: Poorly designed concrete mixes with low cement or high sand content may not thicken satisfactorily with Slump Reducer 1000P.

WARNINGS: Avoid breathing dust. Wear protective clothing and safety glasses during application. Keep away from food and drink. Do not take internally. Refer to product M.S.D.S. (Material Safety Data Sheet) for further health and safety information. FOR INDUSTRIAL USE ONLY. KEEP OUT OF REACH OF CHILDREN.

H.M.I.S. CODES: HEALTH = 1, FLAMMABILITY= 0, REACTIVITY = 0, PERSONAL PROTECTION = C (GLOVES, GOGGLES, APRON)

SHIPPING NAME: Concrete Admixture – Powder - Not regulated by D.O.T.

PACKAGING: 8 ounce (227 gram) pre-measured heat-sealed poly bags, packed 60 / case

STORAGE: Store in a dry, protected area **SHelf LIFE:** Indefinite, properly stored

LIMITED WARRANTY: This product is warranted to be of merchantable quality when used according to the instruction herein. It is not warranted to be suitable for any purpose or use other than the general purpose for which it is intended. Liability under this warranty is limited to the replacement of the product as purchased, if found to be defective upon inspection by the manufacturer. This limited warranty is issued and accepted in lieu of all other expressed warranties and explicitly excludes liability for consequential damages. Buyer assumes all risk and liability resulting from the use of this product. Revised -03-10-09