

W-42 SL HIGH RANGE S.C.C. BASED SUPERPLASTICIZER

PRODUCT DESCRIPTION: Specco W-42 SL plasticizer is a modified polycarboxylated high range water reducing admixtures formulated to produce self-compacting type (S.C.C.) concrete. W-42 SL plasticizer is specifically intended for use in precast and ready mix concrete providing high workability, slightly extended slump life, and improved fluidity with reduced or minimal vibration. The improved dispersing action of W-42 SL plasticizer results in concrete with “self placing” properties that surpass conventional superplasticizer benefits. Very low water to cement ratios can be obtained with as much as 25-30% total water reduction.

BENEFITS: GREATER WATER REDUCTION AND LOWER DOSAGE RATES THAN TRADITIONAL MELAMINE OR NAPHTHALENE BASED SUPERPLASTICIZERS...IMPROVED FLOW (SELF LEVELING) WITH SELF-HEALING RHEOLOGY...HIGH EARLY STRENGTHS...IMPROVED DENSIFICATION OF SURFACES...REDUCTIONS IN VIBRATION AND MANUFACTURING NOISE LEVELS.

COMPOSITION: Modified polycarboxylate polyester solution. W-42 SL plasticizer does not contain any calcium chloride or intentionally added chlorides that would initiate or promote corrosion of reinforcement steel, or contribute to efflorescence.

PHYSICAL PROPERTIES at 70° F (21°C):	APPROXIMATE VALUES:
Weight per gallon:	8.9 +/- 0.2 lb./ gallon
pH:	8.0 +/- 0.5
Color:	Clear light purple solution
Viscosity –Brookfield:	250 +/- 50 cps
Ionic nature:	Anionic

TECHNICAL DATA: W-42 SL plasticizer is formulated to comply with ASTM C-494 requirements for Type F high range water reduction. W-42 SL plasticizer is fully effective and compatible with most concrete admixtures, however, each admixture should be added separately to the concrete mix (see Cautions). By adding fluidity to the mix, W-42 SL plasticizer liquid allows extended workability. The duration of workability depends on temperature, brand and type of cement, aggregate type and gradation, method of mixing, and method of transport. Concrete mixes containing higher overall cement “sulfate” content give easier fluidification of the mix than low sulfate cements. When added at normal dosages, W-42 SL plasticizer will not significantly affect the concrete’s heat of hydration. Specco W-42 SL plasticizer is compatible with most mineral and chemical components common to Portland cement, calcium alumina cement, and calcium sulfate (gypsum)

PERFORMANCE CHARACTERISTICS - Run @ 70°F (21° C) ambient temperature.

MIX DATA:	W-42 SL DOSAGE:
Dosage, fl oz./cwt (ml/100 kg)	6 (520)
Cement, Type I lb/yd ³ (kg/m ³)	500 (296)
Air Content %	Non-Air Entrained

STRENGTH GAIN VERSUS CONTROL- @ 70° F (21° C)

Compressive Strength psi (mPa)	Plain (Control)	W-42 SL @ 6oz/cwt (405 ml /100kg)
1 day	1650 (11.7)	1850 (13.2)
3 day	3100 (22.0)	3575 (25.4)
7 day	3850 (27.4)	4500 (31.3)
28 days	5200 (37.0)	6050 (43.0)

*This data is based on controlled laboratory tests. Slight variations from the results shown here may be experienced as a result of jobsite conditions, different mix design components, or other factors.

DIRECTIONS FOR USE: Specco W-42 SL plasticizer is normally dosed as supplied at a rate of 6-8 ounces per 100 lbs. of cement (390–520ml/100 kg). Other dosages may be required depending on specific conditions. W-42 SL plasticizer's improved flow properties allow typical dosage rates approximately 40% less than of standard melamine and naphthalene based superplasticizers, while maintaining the same percent water reduction.

AIR ENTRAINMENT: Independent lab tests have shown no increased air entrainment effects when using W-42SL at 6 oz/ cwt of cement in the ASTM C-494 non-air entrained series. However, in the air entrained series, higher levels of air entrainment (9-10%) were obtained versus the control when dosed at the same 6 ounce level. Therefore, Specco recommends a minimum 50% reduction of any externally added air entraining agents when using in combination with W-42SL to keep the final air entrainment within the 6-8% specification range.

CAUTIONS: Specco W-42 SL plasticizer should be tested and evaluated with actual materials and blending processes to gauge overall performance and compatibility with mix components. W-42 SL plasticizer is water based and will freeze at 32° F, but may be completely restored by thawing at room temperature and mechanically agitating thoroughly. W-42SL should be stirred before using if the material has set for an extended period (3-6 months).

WARNINGS: Avoid contact with skin and eyes. Wear protective clothing and safety glasses during application. Keep away from food and drink. Do not take internally. Refer to product M.S.D.S. (Material Safety Data Sheet) for further health and safety information. FOR INDUSTRIAL USE ONLY. KEEP OUT OF REACH OF CHILDREN.

H.M.I.S. CODES: HEALTH = 1, FLAMMABILITY= 0, REACTIVITY = 0, PERSONAL PROTECTION = C (GLOVES, GOGGLES, APRON)

SHIPPING NAME: Concrete Admixture – Water base - Not regulated – CAS#-Mixture

STORAGE: Ideal storage is between 60° to 80° F. Keep from freezing.

PACKAGING: 5 gallon (18.9 L) pails, 55 gallon (208 L) drums, 265 gallon (1000 L) containers.

SHELF LIFE: 1 year stored properly.

LIMITED WARRANTY: This product is warranted to be of merchantable quality when used according to the instruction herein. It is not warranted to be suitable for any purpose or use other than the general purpose for which it is intended. Liability under this warranty is limited to the replacement of the product as purchased, if found to be defective upon inspection by the manufacturer. This limited warranty is issued and accepted in lieu of all other expressed warranties and explicitly excludes liability for consequential damages. Buyer assumes all risk and liability resulting from the use of this product.

Revised – 11-07